







**TECHNICAL DATA SHEET**
**PHYSICAL PROPERTIES & PACKAGING (FLOATING MULTILAYER MODULAR FLOORING – 4,8 / 0,3 MM)**




Series & Collections	<b>Woods</b> <ul style="list-style-type: none"> <li>• Nordic Oak Antique</li> <li>• Nordic Oak Grey</li> <li>• Nordic Oak Natural</li> <li>• Nordic Oak Silver</li> <li>• Nordic Oak Light</li> </ul>
Construction Extruded Vinyl Core Pre-Attached Underlayment	4,0 mm (including printfilm) 0,8 mm LDPE
Use	Commercial & Residential
Size	1210 mm x 225 mm
Wear Layer	0.3 mm
Edge Detail	4 sides Micro-Bevel
Finish	Urethane with Ceramic Bead (CB)
Embossing	Natural Timber
Thickness	4,80 mm
Pieces/Carton	8
Coverage/Carton	2,18 m <sup>2</sup>
Coverage/Pallet	44 Cartons/Pallet (95,92 m <sup>2</sup> )
Coverage/Container	24 Pallets/Container (2302,08 m <sup>2</sup> )
Limited Warranty	5 year commercial 15 year residential

**EUROPEAN / INTERNATIONAL STANDARDS – CE CERTIFICATION / TESTING**




Description	Standard	Symbol	Requirements	Results
CE Certification	EN 14041		Refer to Standards Below	Refer to Results Below
Reaction to Fire (and Smoke Production)	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2		<b>B<sub>fl</sub> - s1 Classification</b> Critical Flux: ≥8.0kW/m <sup>2</sup> Flame Spread: ≤150mm within 20s Smoke value as % x min: ≤750	Passes Requirements
Formaldehyde Emission	EN 717-1		<b>Class E1:</b> Release ≤0.124mg/m <sup>3</sup>	Passes Requirements
Content of PCP (Pentachlorophenol)	EN 12673:1999		<5ppm	Passes Requirements
Slip Resistance (Dry)	EN 13893		<b>Class DS:</b> Coefficient of Friction ≥ 0.30	Surpasses Requirements
Static Electrical Propensity	EN 1815, Method A		<b>Antistatic Floor Coverings:</b> ≤2,0kV (Absolute Value)	Passes Requirements/Antistatic

**TECHNICAL DATA SHEET**

**EUROPEAN / INTERNATIONAL STANDARDS – MANUFACTURING & USAGE (EN 16511)**

Description	Standard	Symbol	Requirements	Results
Classification (Level of Use)	EN 16511 EN ISO 10874		<b>Commercial - General (Class 32)</b>	Passes Requirements (Refer to Results Below)
Wear Resistance IP, Method A	EN 13329, Annex E		≥4,000 cycles	Surpasses Requirements
Impact Resistance (Big Ball)	EN 13329+A1, Annex F		No Cracks	Surpasses Requirements
Micro-Scratch Resistance [Class] <sup>3</sup>	EN 16094, Method B	N/A	MSR-A2 /MSR-B1	Passes / Surpasses
Castor Chair Resistance	EN 425		After 25,000 cycles: No Disturbance to the Surface; No Delamination, Cracks, or Disruptions	Passes Requirements
Effect of Furniture Leg	EN 424		No Visible Damage	Passes Requirements
Residual Indentation	EN ISO 24343-1		≤0.15mm	Surpasses Requirements
Resistance to Staining [Grade, per Group]	EN 438-2 (Group 1 & 3 - Only 10 Minutes)		Groups 1, 2 & 3: Grade 5	Passes Requirements
Locking Strength	ISO 24334		Long Side ≥ 2.0kN/m Short Side ≥ 3.5kN/m	Surpasses Requirements
Dimensional Stability Due to Variation of Temperature	EN ISO 23999		≤0.25%	Surpasses Requirements
Thickness (t)	ISO 24337		$\Delta t_{avg} \leq 0.50\text{mm}$ (Versus Nominal) $t_{max} - t_{min} \leq 0.50\text{mm}$	Passes Requirements
Length (l)	ISO 24337		$l \leq 1500\text{mm}$ : $\Delta l \leq 0.5\text{mm}$ $l > 1500\text{mm}$ : $\Delta l \leq 0.3\text{mm/m}$ (Versus Nominal)	Passes Requirements
Width (w)			$\Delta w_{avg} \leq 0.10\text{mm}$ (Versus Nominal) $w_{max} - w_{min} \leq 0.20\text{mm}$	Passes Requirements
Squareness (q)			$q_{max} \leq 0.20\text{mm}$	Passes Requirements
Straightness (s)			$s_{max} \leq 0.30\text{mm/m}$	Passes Requirements
Flatness (f)	ISO 24337	N/A	Maximum Single Values: $f_{w,concave} \leq 0.15\%$ , $f_{w,convex} \leq 0.20\%$ $f_{l,concave} \leq 0.50\%$ , $f_{l,convex} \leq 1.00\%$	Passes Requirements
Openings (o)	ISO 24337	N/A	Measured from the Surface Between Vertical, Contacting Edges: $o_{avg} \leq 0.15\text{mm}$ , $o_{max} \leq 0.20\text{mm}$	Passes Requirements
Height Difference (h)	ISO 24337	N/A	$h_{avg} \leq 0.10\text{mm}$ $h_{max} \leq 0.15\text{mm}$	Passes Requirements

**TECHNICAL DATA SHEET**
**EUROPEAN / INTERNATIONAL STANDARDS – AUXILIARY PERFORMANCE & SAFETY**

Description	Standard	Symbol	Requirements	Results
Colour Fastness to Light	ISO 105-B02, Method 3		≥Grade 6	Passes Requirements
Slip Resistance (Wet)	DIN 51130	N/A	Grade R10: ≥10° and <19°	Surpasses Requirements
Slip Resistance (Australia / New Zealand)	AS 4586	N/A	<b>Wet Pendulum (Slider 96)</b> P4: 45-54 SRV <b>Oil-Wet Inclining Platform</b> Grade R9: ≥6° and <10°	Passes / Surpasses
Slip Resistance (UK)	BS 7976-2+A1	N/A	<u>Ratings - Slip Potential</u> Low: 36+ PTV Moderate: 25-35 PTV High: 0-24 PTV	Low Slip Potential - Dry & Wet
Resistance to Staining	EN ISO 26987:2012		N/A (No Official Requirements)	0 (Not Affected/Unchanged)
Thickness of wear layer	ISO 24340: 2006	N/A	N/A	Surpasses Requirements
Impact Sound Insulation <sup>1</sup>	EN ISO 10140-3 ISO 717-2 EN ISO 140-8		N/A	ΔL <sub>w</sub> = 18 dB
Product-Content Safety	REACH SVHC 191	N/A	Refer to Standard	Passes Requirements

**Footnotes**

1) **Impact Sound Insulation (EN ISO 10140-3, ISO 717-2, EN ISO 140-8):** ΔL<sub>w</sub> = Weighted Reduction of Impact Sound Pressure Level

The manufacturing facility is ISO 9001 (Quality Management System) and ISO 14001 (Environmental Management System) certified.