

## ENVIRONMENTAL PRODUCT DECLARATION



### 3-LAYER WOODEN FLOORBOARDS 1-STRIP AND 3-STRIP



#### EPD program operator

Building Research Institute (ITB), 00-611 Warsaw, Filtrowa 1  
[www.itb.pl](http://www.itb.pl); [energia@itb.pl](mailto:energia@itb.pl)  
ITB is the verified member of The European Platform for EPD program operators  
and LCA practitioners [www.eco-platform.org](http://www.eco-platform.org)

#### MANUFACTURER

BARLINEK INWESTYCJE Sp. z o.o.  
ul. Przemysłowa 1  
74-320 Barlinek, Poland  
tel.: +48 95 7471 300  
fax: +48 95 7479 301  
[office@barlinek.com.pl](mailto:office@barlinek.com.pl)

#### SALES OFFICE

BARLINEK S.A.  
Al. Solidarności 36,  
25-323 Kielce, Poland  
tel.: +48 41 333 11 00  
fax: +48 41 333 00 00  
[info@barlinek.com.pl](mailto:info@barlinek.com.pl)



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.



# ENVIRONMENTAL PRODUCT DECLARATION TYPE III NO. 373/2023

## Basic information

This declaration is the Type III Environmental Product Declaration (EPD) based on EN 15804 + A2 and verified according to ISO 14025 by an external auditor. It contains the information on the impacts of the declared construction materials on the environment and their aspects verified by the independent body according to ISO 14025. Basically, comparison or evaluation of EPD data is possible only if all the compared data were created according to EN 15804 + A2.

|                               |                                                                                                       |
|-------------------------------|-------------------------------------------------------------------------------------------------------|
| Life cycle analysis (LCA):    | A1-A5, B1-B7, C1-C4 and D modules in accordance with<br>EN 15804 + A2 (Cradle to Grave with module D) |
| Year of EPD preparation:      | 2022                                                                                                  |
| Year of EPD validation:       | 2023                                                                                                  |
| Product standard:             | EN 13489:2017-11                                                                                      |
| Reference Service Life (RSL): | > 30 years                                                                                            |
| PCR:                          | ITB-PCR A                                                                                             |
| Declared unit:                | 1 m <sup>2</sup>                                                                                      |
| Reasons for performing LCA:   | B2B                                                                                                   |
| Representativeness:           | Polish, European                                                                                      |

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

## Manufacturer and Product Information

Barlinek Inwestycje Sp. z o.o. is a Polish manufacturer of layered wooden floors with potential production of 10 mln m<sup>2</sup> per annum. The company distributes its products among 55 countries located in 5 continents. As well as the Barlinek floorboards, the group also produces certified flooring for sporting facilities, skirting boards and wood biofuels – wood pellet and fireplace briquette. Barlinek has also initiated many programmes concerning environmental protection and ecological education. For many years now the company has been conducting its 1 for 1 programme, whereby the planting of one tree is co-financed for each purchased pack of Barlinek floorboards marked with a logo of this pro-ecological initiative.

### Barlinek floorboarding:

- possible to lay over underfloor heating
- solid construction
- floor resistant to changes in temperature and humidity
- fast and easy DIY installation
- product ready to use immediately after installation
- possible to renovate



Fig. 1. Cross structure of 3-layer wooden floorboard produced by Barlinek Inwestycje Sp. z o.o.

Barlinek floorboard is made from three layers of real wood arranged in a cross structure (Fig. 1) in order to prevent swelling, squeaking or drying out causing splits. The cross construction reduces natural tension and compression of wood, provides a balance between the layers of the board, and thus guarantees the stability of the floor. The Barlinek floorboard's layered structure is suited for underfloor heating. The floorboards are joined using 5Gc joints and Barclick (Fig. 2) which allow to lay the floor without most of the tools which are usually necessary to install a floor. Specification of the product is shown in Table 1.

### Joints – 5Gc BARLOCK & BARCLIK systems provide:

- fast & easy installation
- reductions of contamination
- possibility to lay again
- reduction of damage risk during installation or dismantling



Fig. 2. Views of Barlinek floorboards with 5Gc BARLOCK and BARCLIK systems

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 1. Specification of 3-layer wooden floorboard produced by Barlinek Inwestycje Sp. z o.o.

## 3-LAYER WOODEN FLOORBOARD

|                            |                                                                                                                                                                                                                                           |
|----------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Series:</b>             | Advance, Décor, Easy Basic, Easy Classic, Life, Pure, Pure Vintage Line, Pure Classico Line, Senses, Sport Extreme, Sport Training, Tastes of Life and others                                                                             |
| <b>Wood species:</b>       | oak, beech, birch, jatobe, ash, maple, merbau, sapele                                                                                                                                                                                     |
| <b>Colour:</b>             | natural, white, brown, light brown, dark brown, smoked effect, cognac, cream, cream white-wash, espresso, gold, graphite, coffee, creamy-beige, honey, olive, grey, walnut, gold-brown, row effect, extreme white, grey beige, oak effect |
| <b>Floor board pattern</b> | 1-strip, 3-strip, 3-strip, 4-strip, 6-strip                                                                                                                                                                                               |
| <b>Length [mm]</b>         | 660, 725, 1092, 1800, 2200                                                                                                                                                                                                                |
| <b>Width [mm]</b>          | 110, 130, 155, 180, 207, 240                                                                                                                                                                                                              |
| <b>Thickness [mm]</b>      | 10, 14, 15, 18                                                                                                                                                                                                                            |

The 3-layer wooden floorboard is offered in two pattern:

- 1-strip: one row of staves along the width of the board (similar appearance to solid floorboard)
- 3-strip: three rows of staves across the width of the board (similar appearance to a traditional floor).



The Barlinek floorboard can be installed in a floating system, that is glueless and based on modern tongue-and-groove joints. It is a method, that allows to install the floor yourself. The floor is also easy to be dismantled or re-installed. An alternative is to install the floor in a traditional way - by gluing the boards to the subfloor, which ensures stability of the installation even on large surfaces. The Barlinek floorboard does not require any additional preservative treatment. The floor is ready for use immediately after installation. The performance of the product is listed in Table 2.



Fig. 3. The view of 3-layer wooden floorboard produced by Barlinek Inwestycje Sp. z o.o. during installation

| Characteristics                     | Declared performance                                                               | Harmonized standard |
|-------------------------------------|------------------------------------------------------------------------------------|---------------------|
| <b>Reaction to fire</b>             | D <sub>fl</sub> – s1, Cfl-s1 for Sport Extreme, finishing with LIF and LIT varnish | EN 14342:2013       |
| <b>Minimal density</b>              | 500 kg/m <sup>3</sup>                                                              |                     |
| <b>Minimal thickness</b>            | 10 mm                                                                              |                     |
| <b>Release of formaldehyde</b>      | E-1                                                                                |                     |
| <b>Content of pentachlorophenol</b> | ≤ 5 ppm                                                                            |                     |
| <b>Thermal conductivity</b>         | 0,14 W/mK                                                                          |                     |

Table 2. Performance of 3-layer wooden floorboard produced by Barlinek Inwestycje Sp. z o.o.

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

## LIFE CYCLE ASSESSMENT (LCA) – general rules applied

### Declared Unit

The declaration refers to declared unit (DU) – 1 m<sup>2</sup> of 3-layer wooden floorboard.

### Allocation

The allocation rules used for this EPD are based on general ITB-PCR A. 3-layer wooden floorboard production is a line process with multiple co-products in one factory located in Barlinek (Poland). Allocation is done on product mass basis. All impacts from raw materials extraction and processing are allocated in A1 module of EPD. 99 % of impacts from line production were inventoried and allocated to all 3-layer wooden floorboard production. Municipal waste and waste water of whole factory were allocated to module A3. Energy supply was inventoried for whole production process. Emissions in Barlinek Inwestycje are measured and were allocated to module A3. Packaging materials were not taken into consideration. They are recycled in a closed loop.

### System limits

The life cycle analysis (LCA) of the declared products covers product stage – modules A1-A5, use stages – modules B1-B7, end of life – modules C1-C4 and benefits and loads beyond the system boundary – module D (Cradle to Grave with module D) in accordance with EN 15804 + A2 and ITB PCR A. The details of systems limits are provided in product technical report. All materials and energy consumption inventoried in factory were included in calculation. Office impacts were also taken into consideration. In the assessment, all significant parameters from gathered production data are considered, i.e. all material used per formulation, utilised thermal energy, internal fuel and electric power consumption, direct production waste, and all available emission measurements. It can be assumed that the total sum of omitted processes does not exceed 5 % of all impact categories. In accordance with EN 15804 + A2, machines and facilities (capital goods) required for the production as well as transportation of employees were not included in LCA.

### Modules A1 and A2: Raw materials supply and transport

Raw materials such as softwood and hardwood logs come from local suppliers while prefabricated elements come from Ukraine, Germany and Russia. Data on transport of the different products to the manufacturing plants is collected and modelled for factory by assessor. Means of transport include small trucks < 10 t (f. ex. couriers) and average truck (10-16 t) are applied. European standards for average combustion were used for calculations.

### Module A3: Production

The Fig. 4 shows the working process during the production of the 3-layer wooden floorboards. The floor manufacturing is basically a three step process including drying, milling and finishing. Green lumber logs are delivered to factory located in Barlinek, where they are fed into a stacking machine prior to kiln drying. Dried lumber then undergoes planing, ripping, trimming and moulding during milling to produce unfinished flooring boards which are further used for the production of 3-layer floorboards. Then the flooring product is sorted by grade and type, packaged and then stored prior to the shipment of the final product. The facility is PN-EN ISO 9001 certified.

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.




Fig. 4. A scheme of the 3-layer wooden floorboard production by Barlinek factory (Poland) v

**The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.**

#### **Modules B1-B7 : Use stages**

In the use stage all impacts related to the use of the 3-layer wooden floorboard over its entire life cycle are presented. This includes provisions for the transport of all materials as well as the energy and water impact associated with use of it. There are no consumables, repair or replacements related to the use of 3-layer wooden floorboard for the period of the reference service life (RLS), hence module B1 and modules B3-B5 have zero impacts.

A scenario was assumed that the floor is oiled/varnished once every three years assuming RLS of 30 years (i.e. ten cycles) and double oil/varnish application. These activities are presented in module B2. Moreover, 3-layer wooden floorboards do not use energy or water during their service life and there are no emissions released from the product during the use.

There are no energy uses to operate building integrated technical systems like energy use for electrical components e.g. electrical motors. Therefore, module B6 has zero impacts. Replacement of the product due to aesthetic reasons (change of interior design) and not related to the loss of performance is not taken into account. Module B7 covers water consumption in the use phase, i.e. the use of domestic hot water and detergent for washing floorboards according to floor care instructions recommended by the manufacturer. The scenario assumes washing the floor once a week and using a floor care agent with a capacity of 500 m<sup>2</sup>/l. Any scenarios included for B1-B7 shall be based on the specific conditions for the RSL.

#### **Modules C1-C4 and D: End-of-life (EoL)**

In the adapted scenario, deconstruction of the 3-layer wooden floorboards is performed with the use of electrical tools (module C1). The resulting waste is transported to a waste processing plant distant about 100 km, on 16-32t lorry EURO 5 (module C2). It is assumed that at the EoL cycle 90% of the 3-layer wooden floorboards are recovered in municipal incineration (module C3) while the residues undergo landfilling (10%) of the wooden floorboards are stored in landfills (module C4). Module D presents credits resulting from the benefits from avoided thermal energy production (gas).

#### **Data quality**

The data selected for LCA originate from ITB-LCI questionnaires completed by Barlinek Inwestycje Sp. z o.o. using the inventory data, ITB and Ecoinvent v. 3.8 databases. No specific data collected is older than five years and no generic datasets used are older than ten years. The representativeness, completeness, reliability, and consistency are judged as good. Polish electricity was calculated based on Ecoinvent v 3.8. supplemented by actual national KOBIZE data.

#### **Data collection period**

Primary data provided by Barlinek Inwestycje Sp. z o.o. covers a period of 01.01.2021 – 31.12.2021 (1 year). The life cycle assessments were prepared for Poland and Europe as reference area.

#### **Assumptions and estimates**

The impacts of the representative 3-layer wooden floorboard were aggregated using weighted average. Impacts were inventoried and calculated for all products in 3-layer wooden floorboard product group.

#### **Calculation rules**

LCA was performed using ITB-LCA tool developed in accordance with EN 15804 + A2.

#### **Databases**

The data for the processes comes from Ecoinvent v. 3.8 and ITB-Database. Specific data quality analysis was a part of external audit.



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

## LIFE CYCLE ASSESSMENT (LCA) - Results

### Declared unit

The declaration refers to declared unit (DU) – 1 m<sup>2</sup> of 3-layer wooden floorboard manufactured by Barlinek Inwestycje Sp. z o.o.

Table 3. System boundaries for the environmental characteristic for 3-layer wooden floorboard manufactured by Barlinek Inwestycje Sp. z o.o.

| Environmental assessment information (MNA – Module not assessed, MD – Module Declared, INA – Indicator Not Assessed) |           |               |                                |                                   |           |             |        |             |               |                        |                       |                           |           |                  |          |                                               |
|----------------------------------------------------------------------------------------------------------------------|-----------|---------------|--------------------------------|-----------------------------------|-----------|-------------|--------|-------------|---------------|------------------------|-----------------------|---------------------------|-----------|------------------|----------|-----------------------------------------------|
| Product stage                                                                                                        |           |               | Construction process           |                                   | Use stage |             |        |             |               |                        |                       | End of life               |           |                  |          | Benefits and loads beyond the system boundary |
| Raw material supply                                                                                                  | Transport | Manufacturing | Transport to construction site | Construction-installation process | Use       | Maintenance | Repair | Replacement | Refurbishment | Operational energy use | Operational water use | Deconstruction demolition | Transport | Waste processing | Disposal | Reuse-recovery-recycling potential            |
| A1                                                                                                                   | A2        | A3            | A4                             | A5                                | B1        | B2          | B3     | B4          | B5            | B6                     | B7                    | C1                        | C2        | C3               | C4       | D                                             |
| MD                                                                                                                   | MD        | MD            | MD                             | MD                                | MD        | MD          | MD     | MD          | MD            | MD                     | MD                    | MD                        | MD        | MD               | MD       | MD                                            |

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 4. LCA results of 3-layer floor board with thickness of 10 mm - environmental impacts (DU = 1m<sup>2</sup>)

| Indicator                                                           | Unit                   | A1        | A2       | A3       | A1-A3     | A4       | A5       | B1       | B2        | B3       |
|---------------------------------------------------------------------|------------------------|-----------|----------|----------|-----------|----------|----------|----------|-----------|----------|
| Global Warming Potential                                            | eq. kg CO <sub>2</sub> | -5.62E+00 | 2.04E+00 | 4.10E+00 | 5.19E-01  | 8.94E-01 | 3.31E-01 | 0.00E+00 | 1.25E+01  | 0.00E+00 |
| Greenhouse gas potential - fossil                                   | eq. kg CO <sub>2</sub> | 2.47E+00  | 2.03E+00 | 4.03E+00 | 8.53E+00  | 8.90E-01 | 3.29E-01 | 0.00E+00 | 8.86E+00  | 0.00E+00 |
| Greenhouse gas potential - biogenic                                 | eq. kg CO <sub>2</sub> | -8.10E+00 | 8.85E-03 | 6.92E-02 | -8.03E+00 | 3.61E-03 | 1.97E-03 | 0.00E+00 | -3.99E+00 | 0.00E+00 |
| Global warming potential - land use and land use change             | eq. kg CO <sub>2</sub> | 1.95E-01  | 1.03E-03 | 1.82E-03 | 1.98E-01  | 4.19E-04 | 1.88E-04 | 0.00E+00 | 7.58E+00  | 0.00E+00 |
| Stratospheric ozone depletion potential                             | eq. kg CFC 11          | 2.99E-07  | 4.53E-07 | 1.77E-07 | 9.30E-07  | 2.00E-07 | 6.72E-08 | 0.00E+00 | 6.07E-07  | 0.00E+00 |
| Soil and water acidification potential                              | eq. mol H+             | 1.37E-02  | 8.03E-03 | 4.13E-02 | 6.31E-02  | 3.54E-03 | 1.43E-03 | 0.00E+00 | 4.87E-02  | 0.00E+00 |
| Eutrophication potential - freshwater                               | eq. kg P               | 8.32E-04  | 1.71E-04 | 6.60E-03 | 7.60E-03  | 6.99E-05 | 7.13E-05 | 0.00E+00 | 1.53E-03  | 0.00E+00 |
| Eutrophication potential - seawater                                 | eq. kg N               | 3.02E-03  | 2.31E-03 | 6.39E-03 | 1.17E-02  | 1.03E-03 | 3.62E-04 | 0.00E+00 | 2.74E-02  | 0.00E+00 |
| Eutrophication potential - terrestrial                              | eq. mol N              | 3.15E-02  | 2.51E-02 | 5.22E-02 | 1.09E-01  | 1.13E-02 | 3.86E-03 | 0.00E+00 | 9.76E-02  | 0.00E+00 |
| Potential for photochemical ozone synthesis                         | eq. kg NMVOC           | 1.19E-02  | 7.76E-03 | 1.66E-02 | 3.63E-02  | 3.46E-03 | 1.20E-03 | 0.00E+00 | 5.01E-02  | 0.00E+00 |
| Potential for depletion of abiotic resources - non-fossil resources | eq. kg Sb              | 2.86E-05  | 1.04E-05 | 4.26E-05 | 8.16E-05  | 4.13E-06 | 1.97E-06 | 0.00E+00 | 4.43E-05  | 0.00E+00 |
| Abiotic depletion potential - fossil fuels                          | MJ                     | 4.48E+01  | 2.98E+01 | 6.70E+01 | 1.42E+02  | 1.30E+01 | 4.84E+00 | 0.00E+00 | 2.29E+02  | 0.00E+00 |
| Water deprivation potential                                         | eq. m <sup>3</sup>     | 1.70E+00  | 1.64E-01 | 2.05E+00 | 3.91E+00  | 6.82E-02 | 3.53E-02 | 0.00E+00 | 9.75E+00  | 0.00E+00 |

| Indicator                                                           | Unit                   | B4       | B5       | B6       | B7        | C1       | C2       | C3       | C4       | D         |
|---------------------------------------------------------------------|------------------------|----------|----------|----------|-----------|----------|----------|----------|----------|-----------|
| Global Warming Potential                                            | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.08E+00  | 2.33E-02 | 1.33E-03 | 1.06E+01 | 8.54E-03 | 5.14E+00  |
| Greenhouse gas potential - fossil                                   | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.01E+00  | 2.28E-02 | 1.33E-03 | 1.14E-01 | 9.93E-04 | -5.39E+0  |
| Greenhouse gas potential - biogenic                                 | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | -2.49E-01 | 4.12E-04 | 4.55E-06 | 1.05E+01 | 7.54E-03 | 1.05E+01  |
| Global warming potential - land use and land use change             | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.38E-02  | 5.37E-06 | 5.22E-07 | 2.95E-05 | 7.30E-07 | -1.87E-04 |
| Stratospheric ozone depletion potential                             | eq. kg CFC 11          | 0.00E+00 | 0.00E+00 | 0.00E+00 | 8.46E-08  | 4.38E-10 | 3.08E-10 | 1.91E-09 | 2.22E-11 | -8.59E-07 |
| Soil and water acidification potential                              | eq. mol H+             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.25E-03  | 2.42E-04 | 5.40E-06 | 1.16E-03 | 6.83E-06 | -4.10E-03 |
| Eutrophication potential - freshwater                               | eq. kg P               | 0.00E+00 | 0.00E+00 | 0.00E+00 | 3.60E-04  | 4.15E-05 | 8.94E-08 | 4.89E-05 | 1.89E-07 | -1.98E-05 |
| Eutrophication potential - seawater                                 | eq. kg N               | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.15E-03  | 3.44E-05 | 1.63E-06 | 6.21E-04 | 3.02E-05 | -8.91E-04 |
| Eutrophication potential - terrestrial                              | eq. mol N              | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.56E-02  | 2.95E-04 | 1.78E-05 | 5.96E-03 | 2.71E-05 | -1.02E-02 |
| Potential for photochemical ozone synthesis                         | eq. kg NMVOC           | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.44E-03  | 8.28E-05 | 5.44E-06 | 1.51E-03 | 1.10E-05 | -4.08E-03 |
| Potential for depletion of abiotic resources - non-fossil resources | eq. kg Sb              | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.28E-05  | 3.30E-08 | 4.71E-09 | 2.21E-07 | 2.06E-09 | -1.64E-06 |
| Abiotic depletion potential - fossil fuels                          | MJ                     | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.69E+01  | 3.73E-01 | 1.97E-02 | 9.56E-01 | 2.07E-02 | -9.30E+01 |
| Water deprivation potential                                         | eq. m <sup>3</sup>     | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.54E+00  | 7.57E-03 | 9.13E-05 | 4.81E-01 | 1.18E-04 | 3.40E-01  |

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 5. LCA results of 3-layer floor board with thickness of 10 mm - the resource use (DU = 1 m<sup>2</sup>)

| Indicator                                                                                                      | Unit           | A1       | A2       | A3       | A1-A3    | A4       | A5       | B1       | B2       | B3       |
|----------------------------------------------------------------------------------------------------------------|----------------|----------|----------|----------|----------|----------|----------|----------|----------|----------|
| Consumption of renewable primary energy - excluding renewable primary energy sources used as raw materials     | MJ             | 8.98E+01 | 5.49E-01 | 2.84E+01 | 1.19E+02 | 2.24E-01 | 1.24E-01 | 0.00E+00 | 5.03E+01 | 0.00E+00 |
| Consumption of renewable primary energy resources used as raw materials                                        | MJ             | 6.86E+01 | 0.00E+00 | 0.00E+00 | 6.86E+01 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.50E+01 | 0.00E+00 |
| Total consumption of renewable primary energy resources                                                        | MJ             | 1.58E+02 | 5.49E-01 | 2.84E+01 | 1.87E+02 | 2.24E-01 | 1.24E-01 | 0.00E+00 | 9.49E+01 | 0.00E+00 |
| Consumption of non-renewable primary energy - excluding renewable primary energy sources used as raw materials | MJ             | 1.04E+01 | 2.98E+01 | 6.61E+01 | 1.06E+02 | 1.30E+01 | 4.86E+00 | 0.00E+00 | 1.63E+02 | 0.00E+00 |
| Consumption of non-renewable primary energy resources used as raw materials                                    | MJ             | 6.58E+00 | 0.00E+00 | 0.00E+00 | 6.58E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.20E+01 | 0.00E+00 |
| Total consumption of non-renewable primary energy resources                                                    | MJ             | 1.70E+01 | 2.98E+01 | 7.04E+01 | 1.17E+02 | 1.30E+01 | 4.86E+00 | 0.00E+00 | 2.15E+02 | 0.00E+00 |
| Consumption of secondary materials                                                                             | kg             | 1.34E-02 | 1.32E-02 | 1.50E-02 | 4.16E-02 | 5.36E-03 | 2.39E-03 | 0.00E+00 | 3.49E-02 | 0.00E+00 |
| Consumption of renewable secondary fuels                                                                       | MJ             | 2.63E-01 | 1.54E-04 | 4.55E-04 | 2.63E-01 | 6.19E-05 | 2.83E-05 | 0.00E+00 | 4.93E-04 | 0.00E+00 |
| Consumption of non-renewable secondary fuels                                                                   | MJ             | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      |
| Net consumption of freshwater resources                                                                        | m <sup>3</sup> | 3.91E-02 | 4.39E-03 | 1.70E-02 | 6.06E-02 | 1.83E-03 | 8.59E-04 | 0.00E+00 | 2.30E-01 | 0.00E+00 |

| Indicator                                                                                                      | Unit           | B4       | B5       | B6       | B7       | C1       | C2       | C3        | C4        | D         |
|----------------------------------------------------------------------------------------------------------------|----------------|----------|----------|----------|----------|----------|----------|-----------|-----------|-----------|
| Consumption of renewable primary energy - excluding renewable primary energy sources used as raw materials     | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.00E+00 | 2.70E-02 | 2.83E-04 | -1.01E+02 | -1.12E+00 | -1.01E+02 |
| Consumption of renewable primary energy resources used as raw materials                                        | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.89E+00 | 0.00E+00 | 0.00E+00 | 1.01E+02  | 1.12E+00  | 1.01E+02  |
| Total consumption of renewable primary energy resources                                                        | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.89E+00 | 2.70E-02 | 2.83E-04 | 2.16E-02  | 4.00E-04  | -2.27E-01 |
| Consumption of non-renewable primary energy - excluding renewable primary energy sources used as raw materials | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.51E+01 | 3.95E-01 | 1.97E-02 | 9.56E-01  | 2.07E-02  | -9.33E+01 |
| Consumption of non-renewable primary energy resources used as raw materials                                    | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.93E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00  | 0.00E+00  | 0.00E+00  |
| Total consumption of non-renewable primary energy resources                                                    | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.70E+01 | 3.95E-01 | 1.97E-02 | 9.56E-01  | 2.07E-02  | -9.33E+01 |
| Consumption of secondary materials                                                                             | kg             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.40E-03 | 3.01E-05 | 6.62E-06 | 2.31E-03  | 7.87E-06  | -2.42E-03 |
| Consumption of renewable secondary fuels                                                                       | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.40E-04 | 1.65E-07 | 7.29E-08 | 5.39E-06  | 2.70E-07  | -9.79E-07 |
| Consumption of non-renewable secondary fuels                                                                   | MJ             | INA      | INA      | INA      | INA      | INA      | INA      | INA       | INA       | INA       |
| Net consumption of freshwater resources                                                                        | m <sup>3</sup> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 3.37E-02 | 1.21E-04 | 2.48E-06 | -1.62E-03 | 2.07E-05  | -5.25E-03 |



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 6. LCA results of 3-layer floor board with thickness of 10 mm – waste categories (DU = 1m<sup>2</sup>)

| Hazardous waste. neutralized     | Unit | A1       | A2       | A3       | A1-A3    | A4       | A5       | B1       | B2       | B3       |
|----------------------------------|------|----------|----------|----------|----------|----------|----------|----------|----------|----------|
| Non-hazardous waste. neutralised | kg   | 1.44E-01 | 4.12E-02 | 3.12E-02 | 2.16E-01 | 1.70E-02 | 7.09E-03 | 0.00E+00 | 2.09E-01 | 0.00E+00 |
| Radioactive waste                | kg   | 3.58E+00 | 7.49E-01 | 1.67E+00 | 6.00E+00 | 3.07E-01 | 1.33E-01 | 0.00E+00 | 5.28E+00 | 0.00E+00 |
| Components for re-use            | kg   | 8.09E-02 | 2.02E-04 | 8.99E-05 | 8.12E-02 | 8.90E-05 | 3.03E-05 | 0.00E+00 | 1.55E-04 | 0.00E+00 |
| Materials for recycling          | kg   | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      |
| Materials for energy recovery    | kg   | 3.20E-04 | 1.08E-04 | 4.87E-03 | 5.29E-03 | 4.50E-05 | 2.03E-05 | 0.00E+00 | 1.07E-03 | 0.00E+00 |
| Energy exported                  | kg   | 1.32E-02 | 8.47E-07 | 2.99E-03 | 1.62E-02 | 3.58E-07 | 1.42E-07 | 0.00E+00 | 2.01E-05 | 0.00E+00 |
| Energy exported                  | MJ   | 1.45E-01 | 3.78E-02 | 1.75E-01 | 3.58E-01 | 1.59E-02 | 7.35E-03 | 0.00E+00 | 6.39E-01 | 0.00E+00 |

| Hazardous waste. neutralized     | Unit | B4       | B5       | B6       | B7       | C1       | C2       | C3       | C4       | D         |
|----------------------------------|------|----------|----------|----------|----------|----------|----------|----------|----------|-----------|
| Non-hazardous waste. neutralised | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.22E-02 | 7.71E-08 | 2.21E-05 | 1.29E-02 | 1.85E-05 | -5.41E-03 |
| Radioactive waste                | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.48E+00 | 2.20E-03 | 3.93E-04 | 6.98E-02 | 5.62E-04 | -2.11E-01 |
| Components for re-use            | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.74E-05 | 3.20E-07 | 1.36E-07 | 2.78E-07 | 6.87E-09 | -1.05E-06 |
| Materials for recycling          | kg   | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA       |
| Materials for energy recovery    | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.29E-03 | 2.26E-06 | 6.11E-08 | 1.00E-05 | 1.59E-07 | -1.16E-05 |
| Energy exported                  | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.71E-03 | 3.17E-09 | 4.94E-10 | 1.40E-07 | 6.97E-10 | -1.84E-07 |
| Energy exported                  | MJ   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.24E-02 | 1.08E-03 | 2.19E-05 | 3.19E-04 | 3.65E-06 | -3.10E-02 |

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 7. LCA results of 3-layer floor board with thickness of 14 mm – environmental impacts (DU = 1m<sup>2</sup>)

| Indicator                                                           | Unit                   | A1        | A2       | A3       | A1-A3     | A4       | A5       | B1       | B2        | B3       |
|---------------------------------------------------------------------|------------------------|-----------|----------|----------|-----------|----------|----------|----------|-----------|----------|
| Global Warming Potential                                            | eq. kg CO <sub>2</sub> | -8.47E+00 | 2.04E+00 | 4.10E+00 | -2.32E+00 | 8.94E-01 | 3.31E-01 | 0.00E+00 | 1.25E+01  | 0.00E+00 |
| Greenhouse gas potential - fossil                                   | eq. kg CO <sub>2</sub> | 2.63E+00  | 2.03E+00 | 4.03E+00 | 8.70E+00  | 8.90E-01 | 3.29E-01 | 0.00E+00 | 8.86E+00  | 0.00E+00 |
| Greenhouse gas potential - biogenic                                 | eq. kg CO <sub>2</sub> | -1.11E+01 | 8.85E-03 | 6.92E-02 | -1.10E+01 | 3.61E-03 | 1.97E-03 | 0.00E+00 | -3.99E+00 | 0.00E+00 |
| Global warming potential - land use and land use change             | eq. kg CO <sub>2</sub> | 1.97E-01  | 1.03E-03 | 1.82E-03 | 2.00E-01  | 4.19E-04 | 1.88E-04 | 0.00E+00 | 7.58E+00  | 0.00E+00 |
| Stratospheric ozone depletion potential                             | eq. kg CFC 11          | 3.02E-07  | 4.53E-07 | 1.77E-07 | 9.33E-07  | 2.00E-07 | 6.72E-08 | 0.00E+00 | 6.07E-07  | 0.00E+00 |
| Soil and water acidification potential                              | eq. mol H <sup>+</sup> | 1.47E-02  | 8.03E-03 | 4.13E-02 | 6.40E-02  | 3.54E-03 | 1.43E-03 | 0.00E+00 | 4.87E-02  | 0.00E+00 |
| Eutrophication potential - freshwater                               | eq. kg P               | 8.89E-04  | 1.71E-04 | 6.60E-03 | 7.66E-03  | 6.99E-05 | 7.13E-05 | 0.00E+00 | 1.53E-03  | 0.00E+00 |
| Eutrophication potential - seawater                                 | eq. kg N               | 3.34E-03  | 2.31E-03 | 6.39E-03 | 1.20E-02  | 1.03E-03 | 3.62E-04 | 0.00E+00 | 2.74E-02  | 0.00E+00 |
| Eutrophication potential - terrestrial                              | eq. mol N              | 3.49E-02  | 2.51E-02 | 5.22E-02 | 1.12E-01  | 1.13E-02 | 3.86E-03 | 0.00E+00 | 9.76E-02  | 0.00E+00 |
| Potential for photochemical ozone synthesis                         | eq. kg NMVOC           | 1.32E-02  | 7.76E-03 | 1.66E-02 | 3.76E-02  | 3.46E-03 | 1.20E-03 | 0.00E+00 | 5.01E-02  | 0.00E+00 |
| Potential for depletion of abiotic resources - non-fossil resources | eq. kg Sb              | 2.89E-05  | 1.04E-05 | 4.26E-05 | 8.19E-05  | 4.13E-06 | 1.97E-06 | 0.00E+00 | 4.43E-05  | 0.00E+00 |
| Abiotic depletion potential - fossil fuels                          | MJ                     | 4.69E+01  | 2.98E+01 | 6.70E+01 | 1.44E+02  | 1.30E+01 | 4.84E+00 | 0.00E+00 | 2.29E+02  | 0.00E+00 |
| Water deprivation potential                                         | eq. m <sup>3</sup>     | 1.76E+00  | 1.64E-01 | 2.05E+00 | 3.97E+00  | 6.82E-02 | 3.53E-02 | 0.00E+00 | 9.75E+00  | 0.00E+00 |

| Indicator                                                           | Unit                   | B4       | B5       | B6       | B7        | C1       | C2       | C3       | C4       | D         |
|---------------------------------------------------------------------|------------------------|----------|----------|----------|-----------|----------|----------|----------|----------|-----------|
| Global Warming Potential                                            | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.08E+00  | 2.33E-02 | 1.33E-03 | 1.06E+01 | 8.54E-03 | 5.14E+00  |
| Greenhouse gas potential - fossil                                   | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.01E+00  | 2.28E-02 | 1.33E-03 | 1.14E-01 | 9.93E-04 | -5.39E+0  |
| Greenhouse gas potential - biogenic                                 | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | -2.49E-01 | 4.12E-04 | 4.55E-06 | 1.05E+01 | 7.54E-03 | 1.05E+01  |
| Global warming potential - land use and land use change             | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.38E-02  | 5.37E-06 | 5.22E-07 | 2.95E-05 | 7.30E-07 | -1.87E-04 |
| Stratospheric ozone depletion potential                             | eq. kg CFC 11          | 0.00E+00 | 0.00E+00 | 0.00E+00 | 8.46E-08  | 4.38E-10 | 3.08E-10 | 1.91E-09 | 2.22E-11 | -8.59E-07 |
| Soil and water acidification potential                              | eq. mol H <sup>+</sup> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.25E-03  | 2.42E-04 | 5.40E-06 | 1.16E-03 | 6.83E-06 | -4.10E-03 |
| Eutrophication potential - freshwater                               | eq. kg P               | 0.00E+00 | 0.00E+00 | 0.00E+00 | 3.60E-04  | 4.15E-05 | 8.94E-08 | 4.89E-05 | 1.89E-07 | -1.98E-05 |
| Eutrophication potential - seawater                                 | eq. kg N               | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.15E-03  | 3.44E-05 | 1.63E-06 | 6.21E-04 | 3.02E-05 | -8.91E-04 |
| Eutrophication potential - terrestrial                              | eq. mol N              | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.56E-02  | 2.95E-04 | 1.78E-05 | 5.96E-03 | 2.71E-05 | -1.02E-02 |
| Potential for photochemical ozone synthesis                         | eq. kg NMVOC           | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.44E-03  | 8.28E-05 | 5.44E-06 | 1.51E-03 | 1.10E-05 | -4.08E-03 |
| Potential for depletion of abiotic resources - non-fossil resources | eq. kg Sb              | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.28E-05  | 3.30E-08 | 4.71E-09 | 2.21E-07 | 2.06E-09 | -1.64E-06 |
| Abiotic depletion potential - fossil fuels                          | MJ                     | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.69E+01  | 3.73E-01 | 1.97E-02 | 9.56E-01 | 2.07E-02 | -9.30E+01 |
| Water deprivation potential                                         | eq. m <sup>3</sup>     | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.54E+00  | 7.57E-03 | 9.13E-05 | 4.81E-01 | 1.18E-04 | 3.40E-01  |



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 8. LCA results of 3-layer floor board with thickness of 14 mm - the resource use (DU = 1 m<sup>2</sup>)

| Indicator                                                                                                      | Unit           | A1       | A2       | A3       | A1-A3    | A4       | A5       | B1       | B2       | B3       |
|----------------------------------------------------------------------------------------------------------------|----------------|----------|----------|----------|----------|----------|----------|----------|----------|----------|
| Consumption of renewable primary energy - excluding renewable primary energy sources used as raw materials     | MJ             | 1.23E+02 | 5.49E-01 | 2.84E+01 | 1.52E+02 | 2.24E-01 | 1.24E-01 | 0.00E+00 | 5.03E+01 | 0.00E+00 |
| Consumption of renewable primary energy resources used as raw materials                                        | MJ             | 9.28E+01 | 0.00E+00 | 0.00E+00 | 9.28E+01 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.50E+01 | 0.00E+00 |
| Total consumption of renewable primary energy resources                                                        | MJ             | 2.16E+02 | 5.49E-01 | 2.84E+01 | 2.45E+02 | 2.24E-01 | 1.24E-01 | 0.00E+00 | 9.49E+01 | 0.00E+00 |
| Consumption of non-renewable primary energy - excluding renewable primary energy sources used as raw materials | MJ             | 1.25E+01 | 2.98E+01 | 6.61E+01 | 1.08E+02 | 1.30E+01 | 4.86E+00 | 0.00E+00 | 1.63E+02 | 0.00E+00 |
| Consumption of non-renewable primary energy resources used as raw materials                                    | MJ             | 6.58E+00 | 0.00E+00 | 0.00E+00 | 6.58E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.20E+01 | 0.00E+00 |
| Total consumption of non-renewable primary energy resources                                                    | MJ             | 1.91E+01 | 2.98E+01 | 7.04E+01 | 1.19E+02 | 1.30E+01 | 4.86E+00 | 0.00E+00 | 2.15E+02 | 0.00E+00 |
| Consumption of secondary materials                                                                             | kg             | 1.52E-02 | 1.32E-02 | 1.50E-02 | 4.34E-02 | 5.36E-03 | 2.39E-03 | 0.00E+00 | 3.49E-02 | 0.00E+00 |
| Consumption of renewable secondary fuels                                                                       | MJ             | 2.63E-01 | 1.54E-04 | 4.55E-04 | 2.64E-01 | 6.19E-05 | 2.83E-05 | 0.00E+00 | 4.93E-04 | 0.00E+00 |
| Consumption of non-renewable secondary fuels                                                                   | MJ             | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      |
| Net consumption of freshwater resources                                                                        | m <sup>3</sup> | 3.98E-02 | 4.39E-03 | 1.70E-02 | 6.12E-02 | 1.83E-03 | 8.59E-04 | 0.00E+00 | 2.30E-01 | 0.00E+00 |

| Indicator                                                                                                      | Unit           | B4       | B5       | B6       | B7       | C1       | C2       | C3        | C4        | D         |
|----------------------------------------------------------------------------------------------------------------|----------------|----------|----------|----------|----------|----------|----------|-----------|-----------|-----------|
| Consumption of renewable primary energy - excluding renewable primary energy sources used as raw materials     | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.00E+00 | 2.70E-02 | 2.83E-04 | -1.01E+02 | -1.12E+00 | -1.01E+02 |
| Consumption of renewable primary energy resources used as raw materials                                        | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.89E+00 | 0.00E+00 | 0.00E+00 | 1.01E+02  | 1.12E+00  | 1.01E+02  |
| Total consumption of renewable primary energy resources                                                        | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.89E+00 | 2.70E-02 | 2.83E-04 | 2.16E-02  | 4.00E-04  | -2.27E-01 |
| Consumption of non-renewable primary energy - excluding renewable primary energy sources used as raw materials | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.51E+01 | 3.95E-01 | 1.97E-02 | 9.56E-01  | 2.07E-02  | -9.33E+01 |
| Consumption of non-renewable primary energy resources used as raw materials                                    | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.93E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00  | 0.00E+00  | 0.00E+00  |
| Total consumption of non-renewable primary energy resources                                                    | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.70E+01 | 3.95E-01 | 1.97E-02 | 9.56E-01  | 2.07E-02  | -9.33E+01 |
| Consumption of secondary materials                                                                             | kg             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.40E-03 | 3.01E-05 | 6.62E-06 | 2.31E-03  | 7.87E-06  | -2.42E-03 |
| Consumption of renewable secondary fuels                                                                       | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.40E-04 | 1.65E-07 | 7.29E-08 | 5.39E-06  | 2.70E-07  | -9.79E-07 |
| Consumption of non-renewable secondary fuels                                                                   | MJ             | INA      | INA      | INA      | INA      | INA      | INA      | INA       | INA       | INA       |
| Net consumption of freshwater resources                                                                        | m <sup>3</sup> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 3.37E-02 | 1.21E-04 | 2.48E-06 | -1.62E-03 | 2.07E-05  | -5.25E-03 |

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 9. LCA results of 3-layer floor board with thickness of 14 mm – waste categories (DU = 1m<sup>2</sup>)

| Indicator                        | Unit | A1       | A2       | A3       | A1-A3    | A4       | A5       | B1       | B2       | B3       |
|----------------------------------|------|----------|----------|----------|----------|----------|----------|----------|----------|----------|
| Hazardous waste. neutralized     | kg   | 1.49E-01 | 4.12E-02 | 3.12E-02 | 2.22E-01 | 1.70E-02 | 7.09E-03 | 0.00E+00 | 2.09E-01 | 0.00E+00 |
| Non-hazardous waste. neutralised | kg   | 3.75E+00 | 7.49E-01 | 1.67E+00 | 6.17E+00 | 3.07E-01 | 1.33E-01 | 0.00E+00 | 5.28E+00 | 0.00E+00 |
| Radioactive waste                | kg   | 8.09E-02 | 2.02E-04 | 8.99E-05 | 8.12E-02 | 8.90E-05 | 3.03E-05 | 0.00E+00 | 1.55E-04 | 0.00E+00 |
| Components for re-use            | kg   | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      |
| Materials for recycling          | kg   | 3.63E-04 | 1.08E-04 | 4.87E-03 | 5.34E-03 | 4.50E-05 | 2.03E-05 | 0.00E+00 | 1.07E-03 | 0.00E+00 |
| Materials for energy recovery    | kg   | 1.32E-02 | 8.47E-07 | 2.99E-03 | 1.62E-02 | 3.58E-07 | 1.42E-07 | 0.00E+00 | 2.01E-05 | 0.00E+00 |
| Energy exported                  | MJ   | 1.47E-01 | 3.78E-02 | 1.75E-01 | 3.60E-01 | 1.59E-02 | 7.35E-03 | 0.00E+00 | 6.39E-01 | 0.00E+00 |

| Indicator                        | Unit | B4       | B5       | B6       | B7       | C1       | C2       | C3       | C4       | D         |
|----------------------------------|------|----------|----------|----------|----------|----------|----------|----------|----------|-----------|
| Hazardous waste. neutralized     | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.22E-02 | 7.71E-08 | 2.21E-05 | 1.29E-02 | 1.85E-05 | -5.41E-03 |
| Non-hazardous waste. neutralised | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.48E+00 | 2.20E-03 | 3.93E-04 | 6.98E-02 | 5.62E-04 | -2.11E-01 |
| Radioactive waste                | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.74E-05 | 3.20E-07 | 1.36E-07 | 2.78E-07 | 6.87E-09 | -1.05E-06 |
| Components for re-use            | kg   | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA       |
| Materials for recycling          | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.29E-03 | 2.26E-06 | 6.11E-08 | 1.00E-05 | 1.59E-07 | -1.16E-05 |
| Materials for energy recovery    | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.71E-03 | 3.17E-09 | 4.94E-10 | 1.40E-07 | 6.97E-10 | -1.84E-07 |
| Energy exported                  | MJ   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.24E-02 | 1.08E-03 | 2.19E-05 | 3.19E-04 | 3.65E-06 | -3.10E-02 |



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 10. LCA results of 3-layer floor board with thickness of 15 mm – environmental impacts (DU = 1 m<sup>2</sup>)

| Indicator                                                           | Unit                   | A1        | A2       | A3       | A1-A3     | A4       | A5       | B1       | B2        | B3       |
|---------------------------------------------------------------------|------------------------|-----------|----------|----------|-----------|----------|----------|----------|-----------|----------|
| Global Warming Potential                                            | eq. kg CO <sub>2</sub> | -9.24E+00 | 2.04E+00 | 4.10E+00 | -3.09E+00 | 8.94E-01 | 3.31E-01 | 0.00E+00 | 1.25E+01  | 0.00E+00 |
| Greenhouse gas potential - fossil                                   | eq. kg CO <sub>2</sub> | 2.68E+00  | 2.03E+00 | 4.03E+00 | 8.74E+00  | 8.90E-01 | 3.29E-01 | 0.00E+00 | 8.86E+00  | 0.00E+00 |
| Greenhouse gas potential - biogenic                                 | eq. kg CO <sub>2</sub> | -1.19E+01 | 8.85E-03 | 6.92E-02 | -1.18E+01 | 3.61E-03 | 1.97E-03 | 0.00E+00 | -3.99E+00 | 0.00E+00 |
| Global warming potential - land use and land use change             | eq. kg CO <sub>2</sub> | 1.98E-01  | 1.03E-03 | 1.82E-03 | 2.01E-01  | 4.19E-04 | 1.88E-04 | 0.00E+00 | 7.58E+00  | 0.00E+00 |
| Stratospheric ozone depletion potential                             | eq. kg CFC 11          | 3.05E-07  | 4.53E-07 | 1.77E-07 | 9.35E-07  | 2.00E-07 | 6.72E-08 | 0.00E+00 | 6.07E-07  | 0.00E+00 |
| Soil and water acidification potential                              | eq. mol H+             | 1.49E-02  | 8.03E-03 | 4.13E-02 | 6.43E-02  | 3.54E-03 | 1.43E-03 | 0.00E+00 | 4.87E-02  | 0.00E+00 |
| Eutrophication potential - freshwater                               | eq. kg P               | 9.04E-04  | 1.71E-04 | 6.60E-03 | 7.68E-03  | 6.99E-05 | 7.13E-05 | 0.00E+00 | 1.53E-03  | 0.00E+00 |
| Eutrophication potential - seawater                                 | eq. kg N               | 3.43E-03  | 2.31E-03 | 6.39E-03 | 1.21E-02  | 1.03E-03 | 3.62E-04 | 0.00E+00 | 2.74E-02  | 0.00E+00 |
| Eutrophication potential - terrestrial                              | eq. mol N              | 3.58E-02  | 2.51E-02 | 5.22E-02 | 1.13E-01  | 1.13E-02 | 3.86E-03 | 0.00E+00 | 9.76E-02  | 0.00E+00 |
| Potential for photochemical ozone synthesis                         | eq. kg NMVOC           | 1.36E-02  | 7.76E-03 | 1.66E-02 | 3.80E-02  | 3.46E-03 | 1.20E-03 | 0.00E+00 | 5.01E-02  | 0.00E+00 |
| Potential for depletion of abiotic resources - non-fossil resources | eq. kg Sb              | 2.90E-05  | 1.04E-05 | 4.26E-05 | 8.20E-05  | 4.13E-06 | 1.97E-06 | 0.00E+00 | 4.43E-05  | 0.00E+00 |
| Abiotic depletion potential - fossil fuels                          | MJ                     | 4.75E+01  | 2.98E+01 | 6.70E+01 | 1.44E+02  | 1.30E+01 | 4.84E+00 | 0.00E+00 | 2.29E+02  | 0.00E+00 |
| Water deprivation potential                                         | eq. m <sup>3</sup>     | 1.78E+00  | 1.64E-01 | 2.05E+00 | 3.99E+00  | 6.82E-02 | 3.53E-02 | 0.00E+00 | 9.75E+00  | 0.00E+00 |


| Indicator                                                           | Unit                   | B4       | B5       | B6       | B7        | C1       | C2       | C3       | C4       | D         |
|---------------------------------------------------------------------|------------------------|----------|----------|----------|-----------|----------|----------|----------|----------|-----------|
| Global Warming Potential                                            | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.08E+00  | 2.33E-02 | 1.33E-03 | 1.06E+01 | 8.54E-03 | 5.14E+00  |
| Greenhouse gas potential - fossil                                   | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.01E+00  | 2.28E-02 | 1.33E-03 | 1.14E-01 | 9.93E-04 | -5.39E+0  |
| Greenhouse gas potential - biogenic                                 | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | -2.49E-01 | 4.12E-04 | 4.55E-06 | 1.05E+01 | 7.54E-03 | 1.05E+01  |
| Global warming potential - land use and land use change             | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.38E-02  | 5.37E-06 | 5.22E-07 | 2.95E-05 | 7.30E-07 | -1.87E-04 |
| Stratospheric ozone depletion potential                             | eq. kg CFC 11          | 0.00E+00 | 0.00E+00 | 0.00E+00 | 8.46E-08  | 4.38E-10 | 3.08E-10 | 1.91E-09 | 2.22E-11 | -8.59E-07 |
| Soil and water acidification potential                              | eq. mol H+             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.25E-03  | 2.42E-04 | 5.40E-06 | 1.16E-03 | 6.83E-06 | -4.10E-03 |
| Eutrophication potential - freshwater                               | eq. kg P               | 0.00E+00 | 0.00E+00 | 0.00E+00 | 3.60E-04  | 4.15E-05 | 8.94E-08 | 4.89E-05 | 1.89E-07 | -1.98E-05 |
| Eutrophication potential - seawater                                 | eq. kg N               | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.15E-03  | 3.44E-05 | 1.63E-06 | 6.21E-04 | 3.02E-05 | -8.91E-04 |
| Eutrophication potential - terrestrial                              | eq. mol N              | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.56E-02  | 2.95E-04 | 1.78E-05 | 5.96E-03 | 2.71E-05 | -1.02E-02 |
| Potential for photochemical ozone synthesis                         | eq. kg NMVOC           | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.44E-03  | 8.28E-05 | 5.44E-06 | 1.51E-03 | 1.10E-05 | -4.08E-03 |
| Potential for depletion of abiotic resources - non-fossil resources | eq. kg Sb              | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.28E-05  | 3.30E-08 | 4.71E-09 | 2.21E-07 | 2.06E-09 | -1.64E-06 |
| Abiotic depletion potential - fossil fuels                          | MJ                     | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.69E+01  | 3.73E-01 | 1.97E-02 | 9.56E-01 | 2.07E-02 | -9.30E+01 |
| Water deprivation potential                                         | eq. m <sup>3</sup>     | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.54E+00  | 7.57E-03 | 9.13E-05 | 4.81E-01 | 1.18E-04 | 3.40E-01  |

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 11. LCA results of 3-layer floor board with thickness of 15 mm - the resource use (DU = 1m<sup>2</sup>)

| Indicator                                                                                                      | Unit           | A1       | A2       | A3       | A1-A3    | A4       | A5       | B1       | B2       | B3       |
|----------------------------------------------------------------------------------------------------------------|----------------|----------|----------|----------|----------|----------|----------|----------|----------|----------|
| Consumption of renewable primary energy - excluding renewable primary energy sources used as raw materials     | MJ             | 1.32E+02 | 5.49E-01 | 2.84E+01 | 1.61E+02 | 2.24E-01 | 1.24E-01 | 0.00E+00 | 5.03E+01 | 0.00E+00 |
| Consumption of renewable primary energy resources used as raw materials                                        | MJ             | 9.93E+01 | 0.00E+00 | 0.00E+00 | 9.93E+01 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.50E+01 | 0.00E+00 |
| Total consumption of renewable primary energy resources                                                        | MJ             | 2.31E+02 | 5.49E-01 | 2.84E+01 | 2.60E+02 | 2.24E-01 | 1.24E-01 | 0.00E+00 | 9.49E+01 | 0.00E+00 |
| Consumption of non-renewable primary energy - excluding renewable primary energy sources used as raw materials | MJ             | 1.31E+01 | 2.98E+01 | 6.61E+01 | 1.09E+02 | 1.30E+01 | 4.86E+00 | 0.00E+00 | 1.63E+02 | 0.00E+00 |
| Consumption of non-renewable primary energy resources used as raw materials                                    | MJ             | 6.58E+00 | 0.00E+00 | 0.00E+00 | 6.58E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.20E+01 | 0.00E+00 |
| Total consumption of non-renewable primary energy resources                                                    | MJ             | 1.96E+01 | 2.98E+01 | 7.04E+01 | 1.20E+02 | 1.30E+01 | 4.86E+00 | 0.00E+00 | 2.15E+02 | 0.00E+00 |
| Consumption of secondary materials                                                                             | kg             | 1.57E-02 | 1.32E-02 | 1.50E-02 | 4.39E-02 | 5.36E-03 | 2.39E-03 | 0.00E+00 | 3.49E-02 | 0.00E+00 |
| Consumption of renewable secondary fuels                                                                       | MJ             | 2.63E-01 | 1.54E-04 | 4.55E-04 | 2.64E-01 | 6.19E-05 | 2.83E-05 | 0.00E+00 | 4.93E-04 | 0.00E+00 |
| Consumption of non-renewable secondary fuels                                                                   | MJ             | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      |
| Net consumption of freshwater resources                                                                        | m <sup>3</sup> | 4.00E-02 | 4.39E-03 | 1.70E-02 | 6.14E-02 | 1.83E-03 | 8.59E-04 | 0.00E+00 | 2.30E-01 | 0.00E+00 |

| Indicator                                                                                                      | Unit           | B4       | B5       | B6       | B7       | C1       | C2       | C3        | C4        | D         |
|----------------------------------------------------------------------------------------------------------------|----------------|----------|----------|----------|----------|----------|----------|-----------|-----------|-----------|
| Consumption of renewable primary energy - excluding renewable primary energy sources used as raw materials     | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.00E+00 | 2.70E-02 | 2.83E-04 | -1.01E+02 | -1.12E+00 | -1.01E+02 |
| Consumption of renewable primary energy resources used as raw materials                                        | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.89E+00 | 0.00E+00 | 0.00E+00 | 1.01E+02  | 1.12E+00  | 1.01E+02  |
| Total consumption of renewable primary energy resources                                                        | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.89E+00 | 2.70E-02 | 2.83E-04 | 2.16E-02  | 4.00E-04  | -2.27E-01 |
| Consumption of non-renewable primary energy - excluding renewable primary energy sources used as raw materials | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.51E+01 | 3.95E-01 | 1.97E-02 | 9.56E-01  | 2.07E-02  | -9.33E+01 |
| Consumption of non-renewable primary energy resources used as raw materials                                    | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.93E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00  | 0.00E+00  | 0.00E+00  |
| Total consumption of non-renewable primary energy resources                                                    | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.70E+01 | 3.95E-01 | 1.97E-02 | 9.56E-01  | 2.07E-02  | -9.33E+01 |
| Consumption of secondary materials                                                                             | kg             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.40E-03 | 3.01E-05 | 6.62E-06 | 2.31E-03  | 7.87E-06  | -2.42E-03 |
| Consumption of renewable secondary fuels                                                                       | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.40E-04 | 1.65E-07 | 7.29E-08 | 5.39E-06  | 2.70E-07  | -9.79E-07 |
| Consumption of non-renewable secondary fuels                                                                   | MJ             | INA      | INA      | INA      | INA      | INA      | INA      | INA       | INA       | INA       |
| Net consumption of freshwater resources                                                                        | m <sup>3</sup> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 3.37E-02 | 1.21E-04 | 2.48E-06 | -1.62E-03 | 2.07E-05  | -5.25E-03 |



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 12. LCA results of 3-layer floor board with thickness of 15 mm – waste categories (DU = 1 m<sup>2</sup>)

| Indicator                        | Unit | A1       | A2       | A3       | A1-A3    | A4       | A5       | B1       | B2       | B3       |
|----------------------------------|------|----------|----------|----------|----------|----------|----------|----------|----------|----------|
| Hazardous waste. neutralized     | kg   | 1.51E-01 | 4.12E-02 | 3.12E-02 | 2.23E-01 | 1.70E-02 | 7.09E-03 | 0.00E+00 | 2.09E-01 | 0.00E+00 |
| Non-hazardous waste. neutralised | kg   | 3.80E+00 | 7.49E-01 | 1.67E+00 | 6.22E+00 | 3.07E-01 | 1.33E-01 | 0.00E+00 | 5.28E+00 | 0.00E+00 |
| Radioactive waste                | kg   | 8.09E-02 | 2.02E-04 | 8.99E-05 | 8.12E-02 | 8.90E-05 | 3.03E-05 | 0.00E+00 | 1.55E-04 | 0.00E+00 |
| Components for re-use            | kg   | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      |
| Materials for recycling          | kg   | 3.73E-04 | 1.08E-04 | 4.87E-03 | 5.35E-03 | 4.50E-05 | 2.03E-05 | 0.00E+00 | 1.07E-03 | 0.00E+00 |
| Materials for energy recovery    | kg   | 1.32E-02 | 8.47E-07 | 2.99E-03 | 1.62E-02 | 3.58E-07 | 1.42E-07 | 0.00E+00 | 2.01E-05 | 0.00E+00 |
| Energy exported                  | MJ   | 1.48E-01 | 3.78E-02 | 1.75E-01 | 3.61E-01 | 1.59E-02 | 7.35E-03 | 0.00E+00 | 6.39E-01 | 0.00E+00 |

| Indicator                        | Unit | B4       | B5       | B6       | B7       | C1       | C2       | C3       | C4       | D         |
|----------------------------------|------|----------|----------|----------|----------|----------|----------|----------|----------|-----------|
| Hazardous waste. neutralized     | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.22E-02 | 7.71E-08 | 2.21E-05 | 1.29E-02 | 1.85E-05 | -5.41E-03 |
| Non-hazardous waste. neutralised | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.48E+00 | 2.20E-03 | 3.93E-04 | 6.98E-02 | 5.62E-04 | -2.11E-01 |
| Radioactive waste                | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.74E-05 | 3.20E-07 | 1.36E-07 | 2.78E-07 | 6.87E-09 | -1.05E-06 |
| Components for re-use            | kg   | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA       |
| Materials for recycling          | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.29E-03 | 2.26E-06 | 6.11E-08 | 1.00E-05 | 1.59E-07 | -1.16E-05 |
| Materials for energy recovery    | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.71E-03 | 3.17E-09 | 4.94E-10 | 1.40E-07 | 6.97E-10 | -1.84E-07 |
| Energy exported                  | MJ   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.24E-02 | 1.08E-03 | 2.19E-05 | 3.19E-04 | 3.65E-06 | -3.10E-02 |

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 13. LCA results of 3-layer floor board with thickness of 18 mm – environmental impacts (DU = 1 m<sup>2</sup>)

| Indicator                                                           | Unit                   | A1        | A2       | A3       | A1-A3     | A4       | A5       | B1       | B2        | B3       |
|---------------------------------------------------------------------|------------------------|-----------|----------|----------|-----------|----------|----------|----------|-----------|----------|
| Global Warming Potential                                            | eq. kg CO <sub>2</sub> | -1.17E+01 | 2.04E+00 | 4.10E+00 | -5.56E+00 | 8.94E-01 | 3.31E-01 | 0.00E+00 | 1.25E+01  | 0.00E+00 |
| Greenhouse gas potential - fossil                                   | eq. kg CO <sub>2</sub> | 2.81E+00  | 2.03E+00 | 4.03E+00 | 8.87E+00  | 8.90E-01 | 3.29E-01 | 0.00E+00 | 8.86E+00  | 0.00E+00 |
| Greenhouse gas potential - biogenic                                 | eq. kg CO <sub>2</sub> | -1.45E+01 | 8.85E-03 | 6.92E-02 | -1.45E+01 | 3.61E-03 | 1.97E-03 | 0.00E+00 | -3.99E+00 | 0.00E+00 |
| Global warming potential - land use and land use change             | eq. kg CO <sub>2</sub> | 2.00E-01  | 1.03E-03 | 1.82E-03 | 2.03E-01  | 4.19E-04 | 1.88E-04 | 0.00E+00 | 7.58E+00  | 0.00E+00 |
| Stratospheric ozone depletion potential                             | eq. kg CFC 11          | 3.17E-07  | 4.53E-07 | 1.77E-07 | 9.47E-07  | 2.00E-07 | 6.72E-08 | 0.00E+00 | 6.07E-07  | 0.00E+00 |
| Soil and water acidification potential                              | eq. mol H+             | 1.57E-02  | 8.03E-03 | 4.13E-02 | 6.50E-02  | 3.54E-03 | 1.43E-03 | 0.00E+00 | 4.87E-02  | 0.00E+00 |
| Eutrophication potential - freshwater                               | eq. kg P               | 9.56E-04  | 1.71E-04 | 6.60E-03 | 7.73E-03  | 6.99E-05 | 7.13E-05 | 0.00E+00 | 1.53E-03  | 0.00E+00 |
| Eutrophication potential - seawater                                 | eq. kg N               | 3.69E-03  | 2.31E-03 | 6.39E-03 | 1.24E-02  | 1.03E-03 | 3.62E-04 | 0.00E+00 | 2.74E-02  | 0.00E+00 |
| Eutrophication potential - terrestrial                              | eq. mol N              | 3.85E-02  | 2.51E-02 | 5.22E-02 | 1.16E-01  | 1.13E-02 | 3.86E-03 | 0.00E+00 | 9.76E-02  | 0.00E+00 |
| Potential for photochemical ozone synthesis                         | eq. kg NMVOC           | 1.49E-02  | 7.76E-03 | 1.66E-02 | 3.92E-02  | 3.46E-03 | 1.20E-03 | 0.00E+00 | 5.01E-02  | 0.00E+00 |
| Potential for depletion of abiotic resources - non-fossil resources | eq. kg Sb              | 2.94E-05  | 1.04E-05 | 4.26E-05 | 8.24E-05  | 4.13E-06 | 1.97E-06 | 0.00E+00 | 4.43E-05  | 0.00E+00 |
| Abiotic depletion potential - fossil fuels                          | MJ                     | 4.93E+01  | 2.98E+01 | 6.70E+01 | 1.46E+02  | 1.30E+01 | 4.84E+00 | 0.00E+00 | 2.29E+02  | 0.00E+00 |
| Water deprivation potential                                         | eq. m <sup>3</sup>     | 1.84E+00  | 1.64E-01 | 2.05E+00 | 4.05E+00  | 6.82E-02 | 3.53E-02 | 0.00E+00 | 9.75E+00  | 0.00E+00 |

| Indicator                                                           | Unit                   | B4       | B5       | B6       | B7        | C1       | C2       | C3       | C4       | D         |
|---------------------------------------------------------------------|------------------------|----------|----------|----------|-----------|----------|----------|----------|----------|-----------|
| Global Warming Potential                                            | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.08E+00  | 2.33E-02 | 1.33E-03 | 1.06E+01 | 8.54E-03 | 5.14E+00  |
| Greenhouse gas potential - fossil                                   | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.01E+00  | 2.28E-02 | 1.33E-03 | 1.14E-01 | 9.93E-04 | -5.39E+0  |
| Greenhouse gas potential - biogenic                                 | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | -2.49E-01 | 4.12E-04 | 4.55E-06 | 1.05E+01 | 7.54E-03 | 1.05E+01  |
| Global warming potential - land use and land use change             | eq. kg CO <sub>2</sub> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.38E-02  | 5.37E-06 | 5.22E-07 | 2.95E-05 | 7.30E-07 | -1.87E-04 |
| Stratospheric ozone depletion potential                             | eq. kg CFC 11          | 0.00E+00 | 0.00E+00 | 0.00E+00 | 8.46E-08  | 4.38E-10 | 3.08E-10 | 1.91E-09 | 2.22E-11 | -8.59E-07 |
| Soil and water acidification potential                              | eq. mol H+             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.25E-03  | 2.42E-04 | 5.40E-06 | 1.16E-03 | 6.83E-06 | -4.10E-03 |
| Eutrophication potential - freshwater                               | eq. kg P               | 0.00E+00 | 0.00E+00 | 0.00E+00 | 3.60E-04  | 4.15E-05 | 8.94E-08 | 4.89E-05 | 1.89E-07 | -1.98E-05 |
| Eutrophication potential - seawater                                 | eq. kg N               | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.15E-03  | 3.44E-05 | 1.63E-06 | 6.21E-04 | 3.02E-05 | -8.91E-04 |
| Eutrophication potential - terrestrial                              | eq. mol N              | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.56E-02  | 2.95E-04 | 1.78E-05 | 5.96E-03 | 2.71E-05 | -1.02E-02 |
| Potential for photochemical ozone synthesis                         | eq. kg NMVOC           | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.44E-03  | 8.28E-05 | 5.44E-06 | 1.51E-03 | 1.10E-05 | -4.08E-03 |
| Potential for depletion of abiotic resources - non-fossil resources | eq. kg Sb              | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.28E-05  | 3.30E-08 | 4.71E-09 | 2.21E-07 | 2.06E-09 | -1.64E-06 |
| Abiotic depletion potential - fossil fuels                          | MJ                     | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.69E+01  | 3.73E-01 | 1.97E-02 | 9.56E-01 | 2.07E-02 | -9.30E+01 |
| Water deprivation potential                                         | eq. m <sup>3</sup>     | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.54E+00  | 7.57E-03 | 9.13E-05 | 4.81E-01 | 1.18E-04 | 3.40E-01  |



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 14. LCA results of 3-layer floor board with thickness of 18 mm - the resource use (DU = 1m<sup>2</sup>)

| Indicator                                                                                                      | Unit           | A1       | A2       | A3       | A1-A3    | A4       | A5       | B1       | B2       | B3       |
|----------------------------------------------------------------------------------------------------------------|----------------|----------|----------|----------|----------|----------|----------|----------|----------|----------|
| Consumption of renewable primary energy - excluding renewable primary energy sources used as raw materials     | MJ             | 1.60E+02 | 5.49E-01 | 2.84E+01 | 1.89E+02 | 2.24E-01 | 1.24E-01 | 0.00E+00 | 5.03E+01 | 0.00E+00 |
| Consumption of renewable primary energy resources used as raw materials                                        | MJ             | 1.20E+02 | 0.00E+00 | 0.00E+00 | 1.20E+02 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.50E+01 | 0.00E+00 |
| Total consumption of renewable primary energy resources                                                        | MJ             | 2.80E+02 | 5.49E-01 | 2.84E+01 | 3.09E+02 | 2.24E-01 | 1.24E-01 | 0.00E+00 | 9.49E+01 | 0.00E+00 |
| Consumption of non-renewable primary energy - excluding renewable primary energy sources used as raw materials | MJ             | 1.49E+01 | 2.98E+01 | 6.61E+01 | 1.11E+02 | 1.30E+01 | 4.86E+00 | 0.00E+00 | 1.63E+02 | 0.00E+00 |
| Consumption of non-renewable primary energy resources used as raw materials                                    | MJ             | 6.58E+00 | 0.00E+00 | 0.00E+00 | 6.58E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00 | 7.20E+01 | 0.00E+00 |
| Total consumption of non-renewable primary energy resources                                                    | MJ             | 2.15E+01 | 2.98E+01 | 7.04E+01 | 1.22E+02 | 1.30E+01 | 4.86E+00 | 0.00E+00 | 2.15E+02 | 0.00E+00 |
| Consumption of secondary materials                                                                             | kg             | 1.72E-02 | 1.32E-02 | 1.50E-02 | 4.54E-02 | 5.36E-03 | 2.39E-03 | 0.00E+00 | 3.49E-02 | 0.00E+00 |
| Consumption of renewable secondary fuels                                                                       | MJ             | 2.63E-01 | 1.54E-04 | 4.55E-04 | 2.64E-01 | 6.19E-05 | 2.83E-05 | 0.00E+00 | 4.93E-04 | 0.00E+00 |
| Consumption of non-renewable secondary fuels                                                                   | MJ             | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      |
| Net consumption of freshwater resources                                                                        | m <sup>3</sup> | 4.07E-02 | 4.39E-03 | 1.70E-02 | 6.21E-02 | 1.83E-03 | 8.59E-04 | 0.00E+00 | 2.30E-01 | 0.00E+00 |

| Indicator                                                                                                      | Unit           | B4       | B5       | B6       | B7       | C1       | C2       | C3        | C4        | D         |
|----------------------------------------------------------------------------------------------------------------|----------------|----------|----------|----------|----------|----------|----------|-----------|-----------|-----------|
| Consumption of renewable primary energy - excluding renewable primary energy sources used as raw materials     | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.00E+00 | 2.70E-02 | 2.83E-04 | -1.01E+02 | -1.12E+00 | -1.01E+02 |
| Consumption of renewable primary energy resources used as raw materials                                        | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.89E+00 | 0.00E+00 | 0.00E+00 | 1.01E+02  | 1.12E+00  | 1.01E+02  |
| Total consumption of renewable primary energy resources                                                        | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.89E+00 | 2.70E-02 | 2.83E-04 | 2.16E-02  | 4.00E-04  | -2.27E-01 |
| Consumption of non-renewable primary energy - excluding renewable primary energy sources used as raw materials | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.51E+01 | 3.95E-01 | 1.97E-02 | 9.56E-01  | 2.07E-02  | -9.33E+01 |
| Consumption of non-renewable primary energy resources used as raw materials                                    | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.93E+00 | 0.00E+00 | 0.00E+00 | 0.00E+00  | 0.00E+00  | 0.00E+00  |
| Total consumption of non-renewable primary energy resources                                                    | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.70E+01 | 3.95E-01 | 1.97E-02 | 9.56E-01  | 2.07E-02  | -9.33E+01 |
| Consumption of secondary materials                                                                             | kg             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.40E-03 | 3.01E-05 | 6.62E-06 | 2.31E-03  | 7.87E-06  | -2.42E-03 |
| Consumption of renewable secondary fuels                                                                       | MJ             | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.40E-04 | 1.65E-07 | 7.29E-08 | 5.39E-06  | 2.70E-07  | -9.79E-07 |
| Consumption of non-renewable secondary fuels                                                                   | MJ             | INA      | INA      | INA      | INA      | INA      | INA      | INA       | INA       | INA       |
| Net consumption of freshwater resources                                                                        | m <sup>3</sup> | 0.00E+00 | 0.00E+00 | 0.00E+00 | 3.37E-02 | 1.21E-04 | 2.48E-06 | -1.62E-03 | 2.07E-05  | -5.25E-03 |

The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Table 15. LCA results of 3-layer floor board with thickness of 18 mm – waste categories (DU = 1 m<sup>2</sup>)

| Indicator                        | Unit | A1       | A2       | A3       | A1-A3    | A4       | A5       | B1       | B2       | B3       |
|----------------------------------|------|----------|----------|----------|----------|----------|----------|----------|----------|----------|
| Hazardous waste. neutralized     | kg   | 1.56E-01 | 4.12E-02 | 3.12E-02 | 2.28E-01 | 1.70E-02 | 7.09E-03 | 0.00E+00 | 2.09E-01 | 0.00E+00 |
| Non-hazardous waste. neutralised | kg   | 3.94E+00 | 7.49E-01 | 1.67E+00 | 6.36E+00 | 3.07E-01 | 1.33E-01 | 0.00E+00 | 5.28E+00 | 0.00E+00 |
| Radioactive waste                | kg   | 8.09E-02 | 2.02E-04 | 8.99E-05 | 8.12E-02 | 8.90E-05 | 3.03E-05 | 0.00E+00 | 1.55E-04 | 0.00E+00 |
| Components for re-use            | kg   | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      |
| Materials for recycling          | kg   | 4.00E-04 | 1.08E-04 | 4.87E-03 | 5.37E-03 | 4.50E-05 | 2.03E-05 | 0.00E+00 | 1.07E-03 | 0.00E+00 |
| Materials for energy recovery    | kg   | 1.32E-02 | 8.47E-07 | 2.99E-03 | 1.62E-02 | 3.58E-07 | 1.42E-07 | 0.00E+00 | 2.01E-05 | 0.00E+00 |
| Energy exported                  | MJ   | 1.54E-01 | 3.78E-02 | 1.75E-01 | 3.67E-01 | 1.59E-02 | 7.35E-03 | 0.00E+00 | 6.39E-01 | 0.00E+00 |

| Indicator                        | Unit | B4       | B5       | B6       | B7       | C1       | C2       | C3       | C4       | D         |
|----------------------------------|------|----------|----------|----------|----------|----------|----------|----------|----------|-----------|
| Hazardous waste. neutralized     | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 4.22E-02 | 7.71E-08 | 2.21E-05 | 1.29E-02 | 1.85E-05 | -5.41E-03 |
| Non-hazardous waste. neutralised | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.48E+00 | 2.20E-03 | 3.93E-04 | 6.98E-02 | 5.62E-04 | -2.11E-01 |
| Radioactive waste                | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.74E-05 | 3.20E-07 | 1.36E-07 | 2.78E-07 | 6.87E-09 | -1.05E-06 |
| Components for re-use            | kg   | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA      | INA       |
| Materials for recycling          | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 1.29E-03 | 2.26E-06 | 6.11E-08 | 1.00E-05 | 1.59E-07 | -1.16E-05 |
| Materials for energy recovery    | kg   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 2.71E-03 | 3.17E-09 | 4.94E-10 | 1.40E-07 | 6.97E-10 | -1.84E-07 |
| Energy exported                  | MJ   | 0.00E+00 | 0.00E+00 | 0.00E+00 | 5.24E-02 | 1.08E-03 | 2.19E-05 | 3.19E-04 | 3.65E-06 | -3.10E-02 |



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

Verification

The process of verification of this EPD is in accordance with ISO 14025 and ISO 21930.  
After verification, this EPD is valid for a 5-year-period. EPD does not have to be recalculated after 5 years, if the underlying data have not changed significantly.

|                                                                                                                                                                                                                        |
|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| The basis for LCA analysis was EN 15804 + A2 and ITB PCR A                                                                                                                                                             |
| Independent verification corresponding to ISO 14025 (subclause 8.1.3)<br><div><input checked="" type="checkbox"/> external <input type="checkbox"/> internal</div>                                                     |
| <p><b>External verification of EPD:</b> Halina Prejzner, PhD Eng</p> <p><b>LCA, LCI audit and input data verification:</b> Mateusz Kozicki, PhD</p> <p><b>Verification of LCA:</b> Michał Piasecki, PhD, D.Sc. Eng</p> |

Note 1: The declaration owner has the sole ownership, liability and responsibility for the for the information provided and contained in EPD. Declarations within the same product category but from different programs may not be comparable. Declarations of construction products may not be comparable if they do not comply with EN 15804 + A2. For further information about comparability, see EN 15804 + A2 and ISO 14025. Depending on the application, a corresponding conversion factor such as the specific weight per surface area must be taken into consideration.

Note 2: ITB is a public Research Organization and Notified Body (EC Reg. no 1488) to the European Commission and to other Member States of the European Union designated for the tasks concerning the assessment of building products' performance. ITB acts as the independent, third-party verification organization (17065/17025 certified). ITB-EPD program is recognized and registered member of The European Platform – Association of EPD program operators and ITB-EPD declarations are registered and stored in the international ECO-PORTAL.



The Barlinek Group is a manufacturer of an engineered flooring. As well as the Barlinek flooring, the Barlinek group also produces certified flooring for sporting facilities, skirting boards and wood biofuels.

#### Normative references

- ITB PCR A General Product Category Rules for Construction Products
- EN 13489:2017 Wood-flooring and parquet - Multi-layer parquet elements
- ISO 14025:2006, Environmental labels and declarations – Type III environmental declarations
  - Principles and procedures
- ISO 21930:2017 Sustainability in buildings and civil engineering works – Core rules for environmental product declarations of construction products and services
- ISO 14044:2006 Environmental management – Life cycle assessment – Requirements and guidelines
- ISO 15686-1:2011 Buildings and constructed assets – Service life planning – Part 1: General principles and framework
- ISO 15686-8:2008 Buildings and constructed assets – Service life planning – Part 8: Reference service life and service-life estimation
- EN 15804 + A2: Sustainability of construction works – Environmental product declarations – Core rules for the product category of construction products
- ISO 14067:2018 Greenhouse gases — Carbon footprint of products — Requirements and guidelines for quantification
- PN-EN 15942:2012 Sustainability of construction works – Environmental product declarations – Communication format business-to-business
- KOBIZE Wskaźniki emisyjności CO<sub>2</sub>, SO<sub>2</sub>, NO<sub>x</sub>, CO i pyłu całkowitego dla energii elektrycznej, 2021





**Instytut Techniki Budowlanej**

00-611 Warsaw, Filtrowa 1

**Thermal Physics, Acoustics and Environment Department**  
02-656 Warsaw, Ksawerów 21

# **CERTIFICATE No 373/2023**

## **of TYPE III ENVIRONMENTAL DECLARATION**

Products:

**3-layer wooden floorboards 1-strip and 3-strip**

Manufacturer:

**BARLINEK INWESTYCJE Sp. z o.o.**

ul. Przemysłowa 1, 74-320 Barlinek, Poland

confirms the correctness of the data included in the development of  
Type III Environmental Declaration and accordance with the requirements of the standard

**EN 15804+A2**

**Sustainability of construction works.**

**Environmental product declarations.**

**Core rules for the product category of construction products.**


This certificate, issued on 13<sup>th</sup> October 2023 is valid for 5 years  
or until amendment of mentioned Environmental Declaration

Head of the Thermal Physics, Acoustics  
and Environment Department

  
Agnieszka Winkler-Skalna, PhD



Deputy Director  
for Research and Innovation

  
Krzysztof Kuczyński, PhD

Warsaw, October 2023

