



tesa[®] PRO 74613

Duct Tape

Product Information

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Produktinnhold

- | | | | |
|-----------------|--------------------------|------------------|--------|
| • Bæremateriale | PE-film med PET filament | • Total tykkelse | 175 µm |
| • Klebetype | Syntetisk gummi | | |

Produktsortiment

- | | |
|------------------------|------------|
| • Tilgjengelige farger | grå, svart |
|------------------------|------------|

Egenskaper / ytelsesverdier

- | | | | |
|-------------------------------|-------------|--|--|
| • Bruddforlengelse | 14 % | • Lett å fjerne | Nei |
| • Bruddstyrke | 40 N/cm | • Lett avrulling | medium |
| • Aldringsbestandighet (UV) | medium | • Løsemiddelfri | Ja |
| • Automatisk påsetting | Ja | • Manuel påsetting | Ja |
| • Avrullningskraft n/cm | 3.5 N/cm | • Motstandsdyktig overfor olje og fett | Nei |
| • Bestandig over for saltvann | medium | • Rette avrivningskanter | good |
| • Core diameter | 3 | • Rivebestandig | Ja |
| • Fjernes uten kleberester | Nei | • Skrivbar | Nei |
| • Fuktbestandighet | medium | • Slitstyrkebestandighet | good |
| • Gjennomsiktighet | Nei | • Spennbarhet | 14 % |
| • Hand tearability | good | • Temperaturbestandighet | medium |
| • Kan skrives på | Nei | • Vanntett | Ja |
| • Kjemikaliebestandig | medium | • Velegnede overflater | Jevnt tre, Fliser, De fleste plasttyper, Glass, Metall |
| • Klebeevne | very good | | |
| • Klebekraft | Høy vedheft | • Vevstetthet | 27 count per square inch |
| | | • Water resistance | low |

Klebekraft

- | | | | |
|------------------------------|----------|---------------------|--------|
| • Klebeevne på ru overflater | 5.5 N/cm | • Klebeevne på Stål | 7 N/cm |
|------------------------------|----------|---------------------|--------|



tesa[®] PRO 74613

Duct Tape

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?mp=74613>